

Extraction of zinc:





ore: zinc blende ZnS

method: reduction by C, CO

place: blast furnace

C, CO and H₂ can only reduce the less
reactive metal from its oxide

Step 1: Roasting with hot oxygen



Temp inside furnace $1500^\circ C$

and b.p of zinc is $907^\circ C$

→ so it produced as pure gas must condense.

and other impurities since they have high b.p stay in the furnace.